TATA STEEL



May 2015

Alloy Steels (<1% Nickel) Safety Data Sheet

1. Identification of the Substance and company

1.1 Product identifier

| Other names: | Special purpose alloy steels, including blackplate steel | | | |
|--------------|---|--|--|--|
| Description: | Low alloy steel cast into many forms and also hot and cold rolled with less than 1% nickel present. | | | |

1.2 Relevant identified uses

Used in many applications such as construction, automotive, energy/power, transport, defence and security, engineering, consumer products, lifting and excavating and packaging.

1.3 Details of supplier

| Company: | Tata Steel Long Products PO Box 1, Brigg Road, Scunthorpe, DN16 1BP | Tata Steel Strip Products UK Port Talbot Works, Port Talbot, SA13 2NG | Tata Steel Strip Products IJmuiden, PO Box 10000, 1970 CA, Ijmuiden | Tata Steel Speciality Manchester Road, Stocksbridge, Sheffield, S36 2JA |
|--|---|--|--|--|
| Telephone: | +44 (0) 1724 404040 | +44 (0) 1639 871111 | +31 (0) 251 495883 | +44 (0) 114 2882361 |
| Normal Hours: Commercial / Technical support | | Commercial / Technical support | Commercial / Technical support | Commercial / Technical support |
| Email: | reach@tatasteel.com | reach@tatasteel.com | reach@tatasteel.com | reach@tatasteel.com |

1.4 Emergency contact

| Emorgonovi | Contact Security | Contact Security | Contact Security | Contact Security |
|------------|------------------|------------------|------------------|------------------|
| Emergency: | Department | Department | Department | Department |

2. Hazards Identification

2.1 Classification

Alloy steel (<1% nickel) is defined as an article under REACH However, some of the components do meet the requirements for classification as dangerous according to the Classification, Labelling and Packaging of substances and mixtures (CLP) Regulations (EC 1272/2008). The principal component that meets the classification as dangerous is nickel, please see the table in Section 3.

Activities such as mechanical working, such as dry grinding/sanding, or hot working, such as welding or flame cutting, may give rise to irritant dust/fumes. (From the constituents of the steel and consumables).

2.2 Label elements according to CLP regulations (EC) 1272/2008

No label required, no signal word required.

2.3 Other hazards

Pre-finished steel can have sharp edges and corners, and relevant precautions should be taken when handling and storing. Under normal conditions of use and storage these materials are stable and non-toxic. Some steels may be coated with a non-dangerous oil, prolonged exposure to which may give rise to skin irritation.

3. Composition / information on ingredients

This refers to steels having specified alloying elements such as silicon, chromium, manganese, molybdenum, vanadium, nickel, copper, calcium and aluminium with a combined total concentration of up to 5% w/w, with a specified nickel content less than 1% w/w. The concentrations of the alloying elements will vary according to customer requirements. For more details reference should be made to British or other national/international standards or customer specification. Depending on customer preference there may be a protective or residual coating of oil on the sheet to prevent corrosion during transport/storage. Some products (but not blackplate steel) are supplied with a coating such as primer or bitumen. In such cases additional information will be provided.



Table showing typical composition of alloy Steel (<1% nickel)

| Product area | Substance | EINECS No. | CAS No. | Range (%) by weight | Classification (CLP Regs) |
|-----------------|----------------------|---------------|-----------|------------------------|------------------------------|
| | Iron | 231-096-4 | 7439-89-6 | Balance | Not classified |
| | Carbon | 231-153-3 | 7440-44-0 | 0.1 – 1.1 | Not classified |
| | Manganese | 231-105-1 | 7439-96-5 | 0.2 – 2.0 | Not classified |
| Steel substrate | Chromium | 231-157-3 | 7440-47-3 | 0.1 – 4.0 | Not classified |
| | Molybdenum | 231-107-2 | 7439-98-7 | 0.01 - 1.2 | Not classified |
| | Vanadium | 231-171-1 | 7440-62-2 | 0.04 - 0.7 | Not classified |
| | Nickel (massive*) | 231-111-4 | 7440-02-0 | 0.04 - 0.9 | H350, H372, H317 |
| | Copper | 231-159-6 | 7440-50-8 | 0.03 - 0.3 | Not classified |
| | Aluminium | 231-072-3 | 7429-90-5 | 0.005 - 1.2 | Not classified |

^{*} Massive form covers all sizes/forms above granular

4. First aid measures

4.1 Description of first aid measures

Skin contact: Cuts (lacerations) to the skin from sharp steel edges should be treated as normal cuts and, if required, seek medical

attention. Wash if contaminated with oil coating.

Eye contact: If particles enter the eye, wash the eye with running water for at least ten minutes. Seek medical advice if irritation

ersists.

Inhalation: If hot work such as welding / burning causes exposure to significant concentrations of fume, remove exposed

personnel to fresh air. Seek medical attention if symptoms such as coughing persist.

Ingestion: None required.

4.2 Most important symptoms and effects

The most important symptoms and effects for eye exposure are soreness and irritation.

4.3 Indication of any immediate medical attention or treatment

Immediate medical attention is required if lacerations are deep.

Fire fighting measures

Alloy steel (<1% nickel) is non-flammable and has a melting point of >1 000 ℃.

6. Accidental release measures

Alloy steel (<1% nickel) is sold in solid massive form and an accidental spill could not occur.

7. Handling and Storage

7.1 Handling

Alloy steel (<1% nickel) is sold in many forms, sheet, coils, sections, tube, pipe, plate or as semi-finished products. Care should be taken when handling, as there may be sharp edges present. Where required the use of hard wearing (protective) gloves and overalls should be used to prevent cuts and abrasions. Care should be taken when lifting heavy loads and, where necessary, use appropriate lifting equipment to do so. Coil bundles may be secured by banding straps, which may have been fitted under tension so care should be taken when removing them. Steel products should never be lifted by retaining straps or bands since these may snap and release the load during lifting.

7.2 Storage

Some products may be secured by using straps or bands, which could cause injury to eyes or other injuries when tension is released. There may be sharp edges present, which could cause lacerations. Store in an appropriate facility to prevent damage, use suitable racks or storage pallets. Lifting should always be carried out in a way that prevents injury to operators or damage to the lifting equipment.





8. Exposure controls and personal protection

8.1 Control parameters [occupational exposure limits (OELs)]

Please note these exposure limits are not always directly associated with the product but with possible exposures that may occur when performing certain activities.

OELs (GESTIS International Limit Values Institut fuer Arbeitsschutz der Deutschen Gesetzlichen Unfallversicherung (IFA) & EH40)

| | Substance | | | | | | |
|--|---|------------------------------|---|------------------------------|---|---------------------------|--|
| Country in EU with OEL for the relevant | Iron oxide (Fe ₂ O ₃ & FeO) as iron | | Nickel, water soluble compounds (as Ni) | | Nickel, water insoluble compounds (as Ni) | | |
| substance | 8-h TWA (mg/m³) | STEL (mg/m ³) | 8-h TWA (mg/m³) | STEL (mg/m ³) | 8-h TWA (mg/m³) | STEL (mg/m ³) | |
| Austria | 5.0 (resp) | 10.0 (resp) | 0.1 | | 0.05 | 0.1 | |
| Belgium | 5.0 | | 0.1 | | 0.1 | | |
| Denmark | 3.5 | 7.0 | 0.01 | 0.02 | 0.01 | 0.02 | |
| France | | | | | | | |
| Germany (AGS) | | | | | | | |
| Germany (DFG) | | | | | | | |
| Hungary | 6.0 (resp) | | 0.1 | 0.1 | 0.1 | 0.1 | |
| Poland | 5.0 | 10.0 | | | | | |
| Spain | 5.0 | | 0.1 | | 0.1 | | |
| The Netherlands | | | | | | | |
| United Kingdom | 5.0 | | 0.1 | | 0.5 | | |
| TWA – Time-weighted average measured over an 8-hour period | | | | | | | |

STEL - Short-term exposure limit value - 15-minute duration

Resp - Respirable fraction of dust

| | Substance | | | | | | |
|---|---|-----------------|---------------------------|------------------------------|------------------------------------|---------------------------|--|
| Country in EU with OEL for the relevant | Manganese & inorganic compounds (as Mn) | | Molybdenum | | Chromium (VI) compounds (as Cr) | | |
| substance | 8-h TWA (mg/m³) | STEL (mg/m³) | 8-h TWA (mg/m³) | STEL (mg/m ³) | 8-hTWA (mg/m³) | STEL (mg/m ³) | |
| Austria | 0.5 | 2.0 | 15.0 | 30.0 | 0.05 | 0.2 | |
| Belgium | 0.2 | | 10.0 | | 0.05 | | |
| Denmark | 0.2 | 0.4 | 10.0 | 20.0 | 0.005 | 0.01 | |
| France | | | | | 0.001 | 0.005 | |
| Germany (AGS) | 0.5 | | | | | | |
| Germany (DFG) | 0.2 | | | | | | |
| Hungary | 5.0 | 20.0 | 15.0 | 60.0 | | 0.05 | |
| Poland | 0.3 | | 4.0 | 10.0 | | | |
| Spain | 0.2 | | 10.0 | | 0.01 | | |
| The Netherlands | | | | | 0.025 | 0.05 | |
| United Kingdom | 0.5 | | 10.0 | 20.0 | 0.05 | | |
| TWA – Time-weighted average measured over an 8-hour period | | | | | | | |
| STEL – Short-term exposure limit value – 15-minute duration | | | | | | | |
| Resp - Respirable fraction of dust | | | | | | | |

8.2 Control Measures

Wear suitable gloves, overalls and eye/face protection when handling the pre-finished steel to prevent cuts and abrasions.

Nickel DNEL (derived no-effect level) Long-term (systematic) = 0.05 mg/m³, Acute (local) = 1.6 mg/m³

If hot work activities, such as welding or burning, or mechanical abrasion are to take place local exhaust ventilation (LEV) should be used to remove any fume/dust produced. When using LEV systems the manufacturers instructions and guidance should be followed at all times to maintain sufficient capture velocity and to ensure that the air cleaning system is in good working order. If a large amount of fume is generated and there is a risk that exposures may exceed relevant OELs, suitable and approved personal respiratory equipment (RPE) should be used in conjunction with the LEV. Ori-nasal respirators fitted with either a P2 or P3 filter (EN149: FFP2S / FFP3S) may be





used when fume levels are high, depending on the dust/fume concentration. Manufacturers' directions for use must be followed and, where applicable, an RPE face-fit test should be successfully completed before use.

9. Physical and chemical properties

| Property | Value used |
|------------------------------------|---|
| Physical State at 20 °C/ 1 013 hPa | Solid |
| Form | Alloy steel (<1% nickel) is a hard, dense silver/grey coloured metallic solid |
| Melting point | 1 450-1 520 °C at 1 013 hPa (steel) |
| Boiling point | Not applicable |
| Relative density | 7.85 kg/dm³ at 20 ℃ |
| Vapour pressure | Not applicable steels due to high melting point >1000 °C |
| Surface tension | Not applicable, steels are an inorganic solid with very low aqueous solubility |
| Flash point | Not applicable, steels are an inorganic solid with a high melting point >1000 ℃ |
| Flammability | Non-flammable |
| Explosive properties | Non-explosive |
| Oxidising properties | No |
| Viscosity | Solid |

10. Stability and reactivity

The product is stable under normal conditions. When heated to high temperatures (>1 000° C) it may give rise to fumes (iron oxide and nickel). In contact with strong acids, steels may release gaseous acid decomposition products (e.g. hydrogen, oxides of nitrogen) and metals will be dissolved in the acid. For chromium-containing steels, contact with strong oxidising agents at high pH (e.g. alkaline cleaners at pH 10-14) may result in the formation of Cr (IV) compounds at ambient temperatures.

11. Toxicological information

Under the normal applications of this product, health effects should not occur owing to the low risk of exposure to minimal hazard material. If activities mechanical activities, such as dry grinding or machining, or hot work, such as welding and burning, are carried out dust / fume will be produced which may irritate the respiratory system at high airborne concentrations. The principal route of entry into the body is via inhalation of fume/dust.

Acute toxicity

Exposure to high fume/dust concentrations in air may cause respiratory irritation and can be potentially harmful if inhaled into the body in large amounts over long time periods. This is not expected under normal conditions of use of the product.

Skin corrosion / irritation

Fumes/dust released during mechanical working or hot work are not known to be irritant.

Eye damage / irritation

Fumes/dust released during mechanical working or hot work are not known to be irritant.

Respiratory / Skin sensitisation

Fumes/dust arising from mechanical working or hot work may potentially cause sensitisation owing to the presence of nickel above 0.1%. Skin Sens. 1 H317: May cause an allergic skin reaction (nickel).

Germ cell mutagenicity

No effect.

Carcinogenicity

Nickel is classified as Carc.2 suspected of causing cancer if present above 0.1%.

Reproductive toxicity

No effect.

Repeated dose toxicity - Inhalation

Exposure to iron oxide fume, in excessive concentrations and over long periods of time, may cause a benign condition called siderosis. Repeated inhalation could lead to cumulative effects. This condition is not expected under normal conditions of use of the product. Repeated exposure to dusts and or fumes containing nickel above 0.1% increases the risk of damage to the respiratory system.





12. Ecological information

There are no known harmful effects from the product on the environment. Under normal conditions of use exposure to the environment should not occur.

12.1 Toxicity

No effect.

12.2 Persistence and Degradability

No effect.

12.3 Bioaccumulative potential

No effect.

12.4 Mobility in soil

No effect.

12.5 Results of PBT and vPvB assessment

Alloy steel (<1% nickel) is not PBT or vPvB.

13. Disposal considerations

Steel products are 100% recyclable and should be recycled at "end of life" in all situations.

14. Transport information

Alloy steel (<1% nickel) is not classified as dangerous under CLP Regulations (EC) 1272/2008 so there is no requirement for transport information. None of the sub-headings in this section is applicable for this product.

15. Regulatory information

15.1

Alloy steel (<1% nickel) specifications are covered by numerous ISO standards. All steels covered by this safety data sheet comply with the packaging and packaging waste EC Directive 94/62/EEC on heavy metal content, the Restriction of Hazardous substances directive 2002/95/EC and the End of Life Vehicle directive 2000/53/EC. The iron manufactured and used to produce this steel product has been registered under REACH along with any other component where a registration was required.

15.2

A chemical safety assessment has not been carried out as alloy steel (<1% nickel) is defined as an article under REACH and does not require an assessment, plus it is not classified as dangerous under the CLP Regulations (EC) 1272/2008.

16. Other Information

Revision

This safety data sheet (SDS) has been produced / revised in line with Annex II of the REACH Regulations (2006) as guidance only, as articles do not require a SDS. Information in this safety data sheet is supplied to inform the customer and should be used where necessary.

This revision is the current version dated <u>May 2015</u> Changes: deleted references to Dangerous Substances Directive to comply with June 2015 requirements CLP. Also minor edits.

Previous Versions: August 2012

Hazard and Precautionary Statements according to CLP Regulations (EC)1272/2008):

H317. May cause an allergic skin reaction
H351. Suspected of causing cancer, inhalation
H372. Causes damage to the respiratory tract

References

GESTIS International Limit Values Institut fuer Arbeitsschutz der Deutschen Gesetzlichen Unfallversicherung (IFA) – website: http://www.dguv.de/ifa/Gefahrstoffdatenbanken/GESTIS-Internationale-Grenzwerte-f%C3%BCr-chemische-Substanzen-limit-values-for-chemical-agents/index-2.jsp

EH40 Workplace Exposure Limits, 2005 as amended (2012) – HSE UK ECHA Website

Disclaimer

The information, specifications, procedures, and recommendations herein are presented in good faith and are believed to be accurate and reliable at the date of issue. Where information is taken from supplied items it is the responsibility of the supplier to ensure the accuracy of the data. The individual authors of this safety sheet are deemed to be appropriately competent. This safety data sheet was





constructed using the guidance provided under the REACH regulations ((EC) No 1907/2006) as to the format and information required. For steel articles a safety data sheet is not a legal requirement and is provided for the convenience of downstream users. Occupational exposure limits (OEL) used in this safety data sheet will be EU OELs and where these limits do not exist UK OELs will be the reference limit. No liability can be accepted with regard to the handling, processing or use of the product concerned which, in all cases, shall be in accordance with appropriate regulations and or legislation. Tata Steel Europe gives no warranty or representation as to the accuracy of the information or for the guidance being for, or suitable for, a specific purpose. All implied warranties and conditions are excluded, to the maximum extent permitted by law. Use of this document by any third party is at your own risk. Save to the extent that liability cannot be excluded by law, Tata Steel Europe is in no way responsible or liable for any damage or loss whatsoever arising from the use of or reliance on the information and guidance contained in this document.

